



DRAIN FABRIC

PROPERTY	TEST METHOD	SPECS
Weight	SCALE	8 oz/yd ²
Tensile Strength	ASTM D-4632	205 lbs
Elongation @ Break	ASTM D-4632	50 %
Mullen Burst	ASTM D-3786	400 psi
Puncture Strength	ASTM D-4833	130 lbs
Trapezoidal Tear	ASTM D-4533	85 lbs
Apparent Opening Size	ASTM 0-4751	80 US Sieve
Permittivity	ASTM D-4491	1.40 Sec
UV Resistance, % Retained	ASTM D-4355	70 %
Flow Rate	ASTM D-4491	90 gal/min/sf
Construction		Needle punched Polypropylene Filaments

Note: To the best of our knowledge, these are the typical property values and are intended as guides only, not as specification limits.